

## Hardox 500

### General Product Description

Hardox 500 is an abrasion resistant steel with a nominal hardness of 500 HBW. Typical applications are components and structures subject to wear. For more information on applications see [www.ssab.com](http://www.ssab.com)

#### Available dimensions

Hardox 500 is available in thicknesses of 4 – 80 mm. Hardox 500 Tuf is available in thicknesses of 4 – 65 mm. Both grades are available in widths up to 3350 mm and lengths up to 14630 mm. More detailed information on dimensions is provided in the dimension program at [www.ssab.com](http://www.ssab.com).

### Mechanical Properties

Thickness mm	Hardness HBW min - max <sup>1)</sup>	Typical yield strength MPa, not guaranteed
4 - 32	470 – 530	1250
(32) - 80	450 - 540	1250

<sup>1)</sup> Brinell hardness, HBW, according to EN ISO 6506-1, on a milled surface 0.5 – 3 mm below surface. At least one test specimen per heat and 40 tons. The nominal material thickness will not deviate more than ±15 mm from that of the test specimen.

The plates are through-hardened to a minimum of 90 % of the guaranteed minimum surface hardness.

Impact properties	Hardox 500	Hardox 500 Tuf
Minimum impact energy (J) for transverse tests Charpy V 10x10 mm test specimen <sup>2)</sup>	–	27 J/+20°C

<sup>2)</sup> For thicknesses less than 12 mm, subsize Charpy V-specimens are used. The specified minimum value is then proportional to the cross-sectional area of the test specimen, compared to a full-size specimen (10 x 10 mm). Impact testing according to ISO EN 148 per heat and thickness group. Average of three tests. Single value minimum 70% of specified average. Impact test is performed from 6 mm.

#### Ultrasonic testing

Plates in thickness of 80 mm are delivered in Class E<sub>2</sub>S<sub>2</sub> in accordance with EN 10 160.

### Chemical Composition (heat analysis)

C <sup>*)</sup> Max %	Si <sup>*)</sup> Max %	Mn <sup>*)</sup> Max %	P Max %	S Max %	Cr <sup>*)</sup> Max %	Ni <sup>*)</sup> Max %	Mo <sup>*)</sup> Max %	B <sup>*)</sup> Max %
0.30	0.70	1.60	0.02	0.01	1.50	1.5	0.60	0.004

The steel is grain refined. <sup>\*)</sup> Intentional alloying elements.

#### Maximum carbon equivalent CET (CEV)

Thickness mm	- (5)	5 - (10)	10 - (20)	20 - (40)	40 - 80
CET (CEV)	0.34 (0.49)	0.34 (0.49)	0.41 (0.62)	0.43 (0.64)	0.46 (0.74)

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40} \quad CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

## Tolerances

More detail are given in our brochure 41-General product information Weldox, Hardox, ArmoX and Toolox-UK or on [www.ssab.com](http://www.ssab.com).

### Thickness

Tolerances according to SSAB thickness precision guarantee AccuRollTech.

- AccuRollTech meets the requirements of EN 10 029 Class A, but offers narrower tolerances.

### Length and width

According to SSAB dimension program.

- Tolerances conforms to EN 10 029.

### Shape

Tolerances according to EN 10 029

### Flatness

Tolerances according to SSAB flatness tolerances which are narrower than EN 10 029 Class N (steel type L).

### Surface Properties

According to EN 10 163-2, Class A Subclass 1.

## Delivery Condition

The delivery condition is Quenched. The plates are delivered with sheared or thermally cut edges. Untrimmed edges after agreement.

Delivery requirements can be found in our brochure 41-General product information Weldox, Hardox, ArmoX and Toolox-UK or [www.ssab.com](http://www.ssab.com).

## Fabrication and Other Recommendations

### Welding, bending and machining

Recommendations can be found in our brochures on [www.hardox.com](http://www.hardox.com) or consult Tech Support, [help@ssab.com](mailto:help@ssab.com).

Hardox 500 is not intend for further heat treatment. It has obtained its mechanical properties by quenching and when necessary by means of subsequent tempering. The properties of the delivery condition cannot be retained after exposure to temperatures in excess of 250°C .

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on this product. Grinding, especially of primer coated plates, may produce dust with a high particle concentration.

## Contact and Information

For information, see our brochures on [www.ssab.com](http://www.ssab.com) or consult our Tech Support, [help@ssab.com](mailto:help@ssab.com).