

### WEAR RESISTANT PLATE

Hardox 600 is an abrasion resistant plate with a hardness of 600 HBW, intended for applications requiring an extremely high abrasion resistance.

**Applications** Liners, cutters, feeders, chutes, shredders, hammers, knives etc.

### Chemical Composition (ladle analysis)

Plate thickness mm	C	Si	Mn	P	S	Cr	Ni	Mo	B	CEV typv.	CET typv.
8-30	0,45	0,7	1,00	0,015	0,010	1,2	2,5	0,8	0,004	0,73	0,55
(30)-50	0,47	0,7	1,00	0,015	0,010	1,2	2,5	0,8	0,004	0,84	0,59

$$CEV = C + \frac{Mn}{6} + \frac{Cr+Mo+V}{5} + \frac{Cu+Ni}{15}$$

$$CET = C + \frac{Mn+Mo}{10} + \frac{Cr+Cu}{20} + \frac{Ni}{40}$$

The steel is grain refined.

**Hardness** HBW  
570-640

**Impact Properties**  
Typical value for 20 mm plate thickness

Test temperature °C	Impact energy Charpy-V, longitudinal J
-40 (-40 F)	20

**Testing** Brinell hardness, HBW according to EN ISO 6506-1, on a milled surface 0,5-3 mm below plate surface per heat and 40 tons. The nominal thickness will not deviate more than ± 15 mm from that of the tested plate.

**Delivery Conditions** Q.

**Dimensions** Hardox 600 is supplied in plate thicknesses of 8-50 mm. More detailed information on dimensions is provided in our brochure 41-General product information Weldox, Hardox, Armax and Toolox-UK.

**Tolerances** Thickness tolerances according to SSAB EMEA thickness precision guarantee AccuRollTech™.  
- AccuRollTech™ meets the requirements of EN 10 029 Class A, but offers more narrow tolerances. More detailed information is given in our brochure 41-General product information Weldox, Hardox, Armax and Toolox-UK.  
According to EN 10 029.  
- Tolerances on shape, length and width.  
Hardox 600 is supplied with a flatness tolerance for thickness less than 15 mm of 15 mm/m and for thicknesses 15 - 50 mm of 10 mm/m.

<b>Surface Properties</b>	According to EN 10 163-2 - Requirements according to Class A. - Repair welding is not allowed.
<b>General Technical Delivery Requirement</b>	According to our brochure 41-General product information Weldox, Hardox, Armax and Toolox-UK.
<b>Heat Treatment and Fabrication</b>	<p>Hardox 600 has obtained its mechanical properties by quenching and when necessary by means of subsequent tempering. The properties of the delivery condition can not be retained after exposure to service or preheating temperatures in excess of 250° (480°F). Hardox 600 is not intended for further heat treatment.</p> <p>For information concerning welding and fabrication, see our brochures on <a href="http://www.hardox.com">www.hardox.com</a> or consult our Technical Customer Service.</p> <p>Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on the product. Grinding, especially of primer coated plates, may produce dust with high particle concentration. Our Technical Customer Service Department will provide further information on request.</p>